

F. L. SMIDTH & CO. ENGINEERS

PLANS & MACHINERY

FOR

CEMENT WORKS, BRICK WORKS, LIME WORKS, MORTAR WORKS
AND
MINING INDUSTRIES

ENGINEERING WORKS

IN

COPENHAGEN, LÜBECK & NEW YORK

BRANCH OFFICES
NEW YORK:
50, CHURCH ST., CITY.

PARIS:
5, RUE FÉNELON.

LONDON:
PALACE CHAMBERS,
9, BRIDGE STREET, S. W.

BERLIN:
N. W. 6, SCHIFFBAUERDAMM 29 A.

ST. PETERSBURG:
GOROCHOWAJA 1.

BIELITZ:
(AUSTR. SILESIA)

SOLE-ADDRESS
COPENHAGEN: FOLASMIDTH
LONDON: CHALKINNESS

CODES USED:

A. B. C. CODE, 4TH AND 5TH EDITIONS
THE ENGINEERING TELEGRAPH CODE
LIEBER'S STANDARD TELEGRAPHIC CODE
WESTERN UNION TELEGRAPHIC CODE
(UNIVERSAL EDITION)

CP/HB

ALL AGREEMENTS ARE CONTINGENT UPON STRIKES,
ACCIDENTS, DELAYS OF CARRIERS AND OTHER CAUSES
BEYOND OUR CONTROL.

COPENHAGEN B., 33, VESTERGADE January 16th 1914

Messrs. The Siam Cement Company, Ltd.,

B a n g k o k .

Dear Sirs,

Referring to our letter of the 6th inst. we have to-day the pleasure to communicate to you the result of the test for crushing strength with cement No.2:

Crushing strength

after 7 days:

260 kg/cm²

245 "

265 "

215 "

235 "

244 kg/cm²

L. SMIDTH & Co., COPENHAGEN. 16/1/1914, Messrs. The Siam Cement Co., Bangkok.

SHEET No. 2.

Hoping that this information will be of interest to you, we remain,

Yours truly

for F. L. Smidth & Co.

Carsten Pedersen